

UNCLASSIFIED

AD NUMBER
AD830351
NEW LIMITATION CHANGE
TO Approved for public release, distribution unlimited
FROM Distribution authorized to U.S. Gov't. agencies and their contractors; Critical Technology; APR 1968. Other requests shall be referred to Air Force Materials Lab., Attn: MAAM, Wright-Patterson AFB, OH 45433.
AUTHORITY
Air Force Materials Lab ltr dtd 2 Mar 1972

THIS PAGE IS UNCLASSIFIED

AD830351



UNCLASSIFIED

review

OF RECENT DEVELOPMENTS

Oxidation-Resistant Coatings for Refractory Metals

B. C. Allen • April 17, 1968

is subject to special export controls and such

AFML (MAMM)

W. R. AFB Ohio 45433

COATING DEVELOPMENT FOR COLUMBIUM ALLOYS

Results of an investigation on improving self-regenerative coatings for columbium involving zinc have been reported.⁽¹⁾ One approach was to add a third element (aluminum or nickel) to lower the vapor pressure of zinc. The temperature limit for oxidation resistance was raised about 150 F. Replacement of zinc by magnesium and addition of a third element (copper, nickel, iron, silicon, or antimony) were unsuccessful. Formation of $CbSi_2$ in a molten zinc-aluminum bath in the presence of 5% resulted in oxidation protection for 50 hours at 2400 F. Binary alloying of the substrate with up to 15 percent vanadium, 5 percent chromium, or 5 percent zirconium offered no improvement. However, addition of 10 to 15 percent titanium not only gave about a 10 percent increase in oxidation life, but also eliminated the "silicide pest" behavior at 1100 to 1650 F.

COATING DEVELOPMENT FOR CHROMIUM ALLOYS

Under NASA sponsorship, Chromalloy⁽²⁾ has investigated a variety of pack cementation aluminum-base coatings for the protection of Cr-5W-0.1Y sheet.⁽³⁾ Of the systems studied, a simple aluminum (Cr_5Al_8 - type) and iron-aluminum [$(Fe-Cr)_xAl_y$ - type] gave the best results. Under cyclic air oxidation, these systems survived over 600 hours at 2100 F, compared with 100 hours for the uncoated alloy. Oxidation life was about 200 hours at 2400 F. Under dynamic conditions of a mach 0.5 flame and 450 rpm rotation, the systems tended to fail in about 100 hours at 2100 F. Protectiveness of the systems was closely related to $AlCr_2O_4$ and $FeO-Al_2Cr_2O_4$ -type spinel formation which also limited nitrogen penetration. By causing substrate recrystallization, the coating process increased the bend ductile-brittle transition temperature (no cracks produced in a 90 to 105-degree bend) from about 500 to 800 F. However, the oxidation exposures raised the transition to above 1600 F, primarily because of aluminum diffusion into the substrate, and secondarily because of atmosphere contamination of the coating.

Also under NASA sponsorship, Battelle-Columbus has investigated protection of Cr-W-0.1Y⁽³⁾ using gas-pressure-bonded alloy foil.⁽⁴⁾ The outer 5 to 10 mil-thick layer consisted of Ni-30Cr or Ni-20Cr-20W which were modified with 3 to 5 percent aluminum in some cases. The study also included barrier layers of molybdenum, W-1ThO₂, W-25Re, and tungsten, with the latter being the most useful in preventing interdiffusion of nickel and chromium. Compatibility layers of platinum or vanadium

between the outer and barrier layers were not beneficial. The outer cladding layers gave cyclic oxidation resistance of over 600 hours at 2100 F and about 100 hours at 2300 F, with the aluminized Ni-20Cr-20W alloy giving the best performance. Rapid oxidation occurred at 2400 F. After exposure for 100 hours at 2100 F, the bend ductile-brittle transition temperature was a minimum of about 1000 F. After exposure at 2300 F, edge cracking was observed and the transition was over 1600 F. The mechanisms of embrittlement included metallic interdiffusion at 2100 F and by both interdiffusion and nitrogen contamination at 2300 F.

COATING PROTECTION FOR THERMIONIC DIODES

In its development of thermionic diodes for operation in hot oxidizing gases, Consolidated Controls is developing coatings for protecting refractory metals.⁽⁵⁾ Elimination of free silicon made possible an impermeable grade of pyrolytic SiC, which appears to be of adequate quality for use at 2550 to 2900 F in air as a barrier envelope. This material demonstrated the required thermal shock qualities, corrosion resistance, and adequate permeation levels. Also developed was a multi-element system consisting of iridium overlaid with CaO-stabilized ZrO₂ for protecting tungsten in air at 3600 F for 2 to 5 hours. The protection concept involved maintenance of a finite partial pressure of iridium oxide within the coating by impeding vaporization.

SPACECRAFT APPLICATIONS

Martin-Marietta has used coated columbium alloys in brazed honeycomb sandwich panels on the lower wing surface of a 1/3-scale model of a high L/D winged reentry vehicle, ASCEP.⁽⁶⁾ Vacuum brazing and coating D-43 alloy with pack cementation TiW Cr-Ti-Si seriously degraded the alloy. Substitution of Sylvania Si-20Cr-5Ti slurry coating gave better coating uniformity and reasonable oxidation protection. However, considerably more effort is required to develop a reliable material-coating system for flight applications.

REFERENCES

- (1) Perlhefter, N., and Lux, B., "Contribution of the Study of Protective Coatings for Columbium Based on Intermetallic Phases", Publications Scientifiques et Techniques du Ministère de l'Air, n° B. S. T. 131, (November 1967).
- (2) Negrin, M., and Block, A., "Protective Coatings for Chromium Alloys", Final report NASA CR-54538, Chromalloy American Corporation, West Nyack, N.Y., Contract NAS 3-7273, (July 1967).
- (3) Goetz, L. J., Hughes, J. R., and Moore, W. F., "The Pilot Production and Evaluation of Chromium Alloy Sheet and Plate", Final Report CR-72184, General Electric Company, Cleveland, O., Contracts NAS 3-7901 and NAS 3-7919, (March 15, 1967).
- (4) Williams, D. N., et al., "Development of Protective Coatings for Chromium-Base Alloys", Report CR-54619, Columbus Laboratories, Battelle Memorial Institute, Columbus, O. Contract NAS 3-7612, (March 5, 1968).
- (5) Engdahl, R. E., and Bedell, J. R., "Two Protective Systems for Refractory Metals Operating in Air at High Temperatures", Consolidated Controls Corporation, Bethel, Conn., paper presented at the Thirteenth Refractory Composites Working Group Meeting, Seattle, Wash., July 18-20, 1967.
- (6) Wilks, C. R., "Advanced Structural Concepts Experimental Program Project ASCEP", Report AFFDL-TR-67-146, Vol. III, Martin-Marietta Corporation, Baltimore, Md., Contract AF 33 (657) - 11539, (November 1967).

DMIC Reviews of Recent Developments present brief summaries of information which has become available to DMIC in the preceding period (usually 3 months), in each of several categories. DMIC does not intend that these reviews be made a part of the permanent technical literature. Copies of referenced reports are not available from DMIC; most can be obtained from the Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314.

DISTRIBUTION FOR		
TEST	WHITE SECTION	<input type="checkbox"/>
DOC	BUFF SECTION	<input checked="" type="checkbox"/>
UNANNOUNCED		<input type="checkbox"/>
JUSTIFICATION.....		
Y		
DISTRIBUTION/AVAILABILITY CODES		
DIST.	AVAIL.	and/or SPECIAL
2		